



GRADE COMPARISON

Unknown Component (024DT) ECONOMY TOP COATED DIRECT THERMAL PAPER (025DT)

		024DT	025DT
Property	Test Method	Typical Value	Typical Value
Basis Weight	TAPPI T410		47.2 lbs / 25X38-500 (3300 Sq Ft) (69.9 g/m ²)
Caliper - Average	TAPPI T411		3.1 mil (78.7 um)
Smoothness (PPS) Print Side	TAPPI T555		1.4 um (1.4 um)
Tear-MD	TAPPI T414		45 grams (441.3 mN)
Tear-CD	TAPPI T414		45 grams (441.3 mN)
Tensile-MD	TAPPI T494		37 lb/inch (6.5 kN/m)
Tensile-CD	TAPPI T494		17 lb/inch (3.0 kN/m)
Stiffness-MD	TAPPI T543		90 Gurley (mg) (.9 mN)
Stiffness-CD	TAPPI T543		35 Gurley (mg) (.3 mN)
Brightness	TAPPI T452		84 % (84.0 %)
Initial Activation Temp	ISO 1924		185 F (85 C)

Issued: 05/29/26

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a la susodicha.



GREEN BAY PACKAGING

COATED PRODUCTS

GRADE COMPARISON

Effective Activation Temp	ISO 1924		230 F (110 C)
Optimum Activation Temp	ISO 1924		300 F (149 C)

Issued: 05/29/26

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.

SPECIALISTS IN COATED SELF-ADHESIVE MATERIALS

3250 South Ridge Road • P. O. Box 19017 • Green Bay, WI 54307-9017 • USA • Phone: (920)-337-1800, 800-445-4269