

PRODUCT INFORMATION

020AC - 2 MIL CLEAR ACETATE

A 2.0 mil clear acetate film with good clarity and printability. It is compostable. Has relatively low tear resistance and is good for tamperproof applications. Meets the ASTM D6400 compost standard.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Average	mil	2.0	um (micrometer)	50.8	TAPPI T411
Gloss	% @ 60 degrees	146	% @ 60 degrees	146.0	ASTM D523
Tensile Film - MD	lb/sq inch	13050	kg/sq cm	917.4	ASTM D882
Elongation at Break - MD	%	35	%	35.0	ASTM D882
Area Yield	sq in/lb	10730	sq m/kg	15.3	ASTM E252

Issued: 09/10/25

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No solespeerson, representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ninaún tipo de garantía, ni hacer representancion alauna contraria a lo susodicho.