

## PRODUCT INFORMATION

## 020AC - 2 MIL CLEAR ACETATE

A 2.0 mil clear acetate film with good clarity and printability. It is compostable. Has relatively low tear resistance and is good for tamperproof applications. Meets the ASTM D6400 compost standard.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Average	mil	2.0	um (micrometer)	50.8	TAPPI T411
Gloss	% @ 60 degrees	146	% @ 60 degrees	146.0	ASTM D523
Tensile Film - MD	lb/sq inch	13050	kg/sq cm	917.4	ASTM D882
Elongation at Break - MD	%	35	%	35.0	ASTM D882
Area Yield	sq in/lb	10730	sq m/kg	15.3	ASTM E252

Issued: 07/22/25

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc., products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No selesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.