

## PRODUCT INFORMATION

## 070MK - 3.0 MIL SYNTHETIC MEDIUM SENSITIVITY FILM

A 3.0 mil BOPP direct thermal film. Medium degree of sensitivity. Top coated for durability. Use when moisture and environmental resistance are important. Dark image for excellent ability to be read and scanned.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	36.2	grams/sq meter	53.6	TAPPI T410
Caliper Average (Films)	mils	3.000	um (micrometers)	76.2	ASTM D374
Tear-MD	grams	27	mN	264.8	TAPPI T414
Tear-CD	grams	20	mN	196.1	TAPPI T414
Stiffness-MD	Gurley (mg)	27	mN	.3	TAPPI T543
Stiffness-CD	Gurley (mg)	39	mN	.4	TAPPI T543
Initial Activation Temp	F	167	С	75	ISO 1924
Effective Activation Temp	F	196	С	91	ISO 1924
Optimum Activation Temp	F	298	С	148	ISO 1924

## Notes

http://gbp.com/coated-direct-thermal-ink-recommendations

Issued: 09/10/25

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No solespesson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.