

## **PRODUCT INFORMATION**

## 026TL

Item #:

S6397560

## 2.6 MIL WHITE TC BOPP

Approximate weight per MMSI: 70 lbs. Standard core size is 3 inches. Total caliper: 2.6 mils +/- 10%

## FACESTOCK

A 2.6 mil glossy white BOPP top coated for ink adhesion. Has a distinctive pearlescent sheen. Excellent compatibility with UV curing inks and water based flexo ink systems. Label-Lyte is a Trademark of Jindal Films America.

| while the carried mass and water based news in Systems. Each Eye is a Trademark of small runs rune red. |                |               |                  |              |             |
|---|----------------|---------------|------------------|--------------|-------------|
| Test Property   | Units          | Typical Value | Metric Units     | Metric Value | Test Method |
| Caliper Average (Films)   | mils           | 2.600         | um (micrometers) | 66.0         | ASTM D374   |
| Gloss - Films   | % @ 45 degrees | 68            | % @ 45 degrees   | 68.0         | ASTM D2457  |
| Opacity - Films   | %              | 89            | %                | 89.0         | ASTM D589   |
| Elongation at Break - MD  | %              | 200           | %                | 200.0        | ASTM D882   |
| Elongation at Break - TD  | %              | 50            | %                | 50.0         | ASTM D882   |
| Area Yield  | sq in/lb       | 14200         | sq m/kg          | 20.3         | ASTM E252   |

Issued: 09/07/25

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No solespector, preventation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ninaún tipo de garantía, ni hacer representancion alauna contraria a lo susodicho.