



PRODUCT INFORMATION

046TV0010340SC

Item #: S6881052

1073D TYVEK/103 PERMANENT ADHESIVE/40 SC LINER

Approximate weight per MMSI: 230 lbs. Standard core size is 3 inches. Total caliper: 10.6 mils +/- 10%

FACESTOCK

DuPont™ Tyvek® (1073D) is a 7.5 mil, strong, translucent polyolefin with exceptional strength and moisture resistance.

DuPont™ and Tyvek® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	50.4	grams/sq meter	74.6	TAPPI T410
Caliper - Average	mils	7.5	um	191	ASTM D1777
Opacity	%	96.0	%	96.0	TAPPI T425
Tear-MD	grams	498.8	mN	4891.6	TAPPI T414
Tear-CD	grams	480.8	mN	4715	TAPPI T414
Tensile-MD	lb/inch	42	kN/m	7.4	ASTM D5035
Tensile-CD	lb/inch	48	kN/m	8.4	ASTM D5035

ADHESIVE

A soft, high performance film label acrylic adhesive with excellent clarity and adhesion to low energy surfaces, along with outstanding wet-out.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.7	um(micrometer)	16.6	
Shear (1 x 1/2 x 1 kg)	hours	2.4	hours	2.4	CPD-55
Peel - 180 D SS 20 min	lb/inch	2.3	grams/25 mm	1026.8	CPD-52
Loop Tack Stain Steel	oz/sq inch	50	kg/645 sq mm	1.4	CPD-16
Min. App. Temp.	F	40	C	4	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

LINER

A white densified kraft sheet 41# (67 g/m²) with excellent point-to-point caliper control.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500 (3000 Sq Ft)	41.0	grams/sq meter	66.8	TAPPI T410
Caliper - Average	mil	2.400	um (micrometer)	61.0	TAPPI T411
Opacity	%	60.0	%	60.0	TAPPI T425
Tear-MD	grams	34.0	mN	333.4	TAPPI T414
Tear-CD	grams	39.0	mN	382.5	TAPPI T414
Tensile-MD	lb/inch	40.0	kN/m	7.0	TAPPI T494
Tensile-CD	lb/inch	17.1	kN/m	3.0	TAPPI T494

Issued: 04/04/25

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.