



PRODUCT INFORMATION

095TK0010315PT

Item #: S6937060

107 MICRON TC KIMDURA/103 PERMANENT ADHESIVE/1.5 MIL CLEAR PET LINER
Approximate weight per MMSI: 229 lbs. Standard core size is 3 inches. Total caliper: 6.32 mils +/- 10%

FACESTOCK

A 4.2 mil Kimdura® BOPP specially top coated for thermal transfer, dot matrix, ion deposition and digital printing.
Registered Trademark of Neenah Paper, Inc. © 2007 NPI All Rights Reserved.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	62.2	grams/sq meter	92.1	TAPPI T410
Caliper - Average	mil	4.2	um (micrometer)	106.7	TAPPI T411
Opacity	%	95.5	%	95.5	TAPPI T425
Smoothness-Wire Side	Sheffield Units	5	Sheffield Units	5.0	TAPPI T538

ADHESIVE

A soft, high performance film label acrylic adhesive with excellent clarity and adhesion to low energy surfaces, along with outstanding wet-out.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Shear (1 x 1/2 x 1 kg)	hours	2.4	hours	2.4	CPD-55
Peel - 180 D SS 20 min	lb/inch	2.3	grams/25 mm	1026.8	CPD-52
Loop Tack Stain Steel	oz/sq inch	50	kg/645 sq mm	1.4	CPD-16
Min. App. Temp.	F	40	C	4	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

LINER

Clear polyester liner with an excellent surface for die-cutting and high speed automatic applications.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	1.42	um (micrometers)	36.1	ASTM D374
Tensile Film - MD	lb/sq inch	32000	kg/sq cm	2249.6	ASTM D882
Tensile Film - TD	lb/sq inch	32000	kg/sq cm	2249.6	ASTM D882
Elongation at Break - MD	%	110	%	110.0	ASTM D882
Elongation at Break - TD	%	110	%	110.0	ASTM D882
Haze	%	6.5	%	6.5	ASTM D1003
Shrinkage-MD	% 30 min @ 302 F	1.5	% 30 min @ 150 C	1.5	ISO 2469
Shrinkage-TD	% 30 min @ 302 F	.4	% 30 min @ 150 C	.4	ISO 2469
Area Yield	sq in/lb	13968	sq m/kg	20.0	ASTM E252

Issued: 04/13/26

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.