



PRODUCT INFORMATION

050ED0070050SC

Item #: S7032060

50# EDP FSC/700 PERMANENT ADHESIVE/3.2 SCK

Approximate weight per MMSI: 252 lbs. Standard core size is 3 inches. Total caliper: 7.5 mils +/- 10%

FACESTOCK

A 50# (74 g/m²) general purpose uncoated paper. Bright white with excellent smudge resistance. Designed for high performance. FSC®-certified paper.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	50	grams/sq meter	74.0	TAPPI T410
Caliper - Average	mil	3.5	um (micrometer)	88.9	TAPPI T411
Opacity	%	87	%	87.0	TAPPI T425
Tear-MD	grams	65	mN	637.4	TAPPI T414
Tear-CD	grams	60	mN	588.4	TAPPI T414
Tensile-MD	lb/inch	25	kN/m	4.4	TAPPI T494
Tensile-CD	lb/inch	18	kN/m	3.2	TAPPI T494
Stiffness Taber-MD	gram cm/mN	1.55	gram cm/mN	1.6	TAPPI T543
Stiffness Taber -CD	gram cm/mN	1.05	gram cm/mN	1.1	TAPPI T543
Brightness	%	92	%	92.0	TAPPI T452

ADHESIVE

A general purpose acrylic emulsion for paper. Repositions on many low energy plastics.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.8	um(micrometer)	20.2	
Shear (1 x 1/2 x 1 kg)	hours	17	hours	17.0	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.2	grams/25 mm	535.7	CPD-52
Loop Tack Stain Steel	oz/sq inch	26	kg/645 sq mm	.7	CPD-16
Min. App. Temp.	F	35	C	2	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

LINER

A white densified kraft sheet 53# (86 g/m²) with excellent point-to-point caliper control.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500 (3000 Sq Ft)	53.5	grams/sq meter	87.2	TAPPI T410
Caliper - Average	mil	3.2	um (micrometer)	81.3	TAPPI T411
Opacity	%	70.0	%	70.0	TAPPI T425
Tear-MD	grams	46.0	mN	451.1	TAPPI T414
Tear-CD	grams	55.0	mN	539.4	TAPPI T414
Tensile-MD	lb/inch	52.0	kN/m	9.1	TAPPI T494
Tensile-CD	lb/inch	24.0	kN/m	4.2	TAPPI T494
Brightness	%	78.0	%	78.0	TAPPI T452

Issued: 04/04/25

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.