



PRODUCT INFORMATION

061DL0050440SC

Item #: S7754060

60# DULL LITHO FSC/504 PERMANENT ADHESIVE/40 SC LINER

Approximate weight per MMSI: 253 lbs. Standard core size is 3 inches. Total caliper: 6.1 mils +/- 10%

FACESTOCK

60# (89 g/m²) high quality, dull finish litho offering excellent print and die-cut properties. Good for flexographic and offset printing. FSC®-certified paper.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	60	grams/sq meter	88.8	TAPPI T410
Caliper - Average	mil	3.0	um (micrometer)	76.2	TAPPI T411
Gloss	%	35	%	35.0	TAPPI T480
Opacity	%	93	%	93.0	TAPPI T425
Smoothness (PPS) Print Side	um	2.1	um	2.1	TAPPI T555
Tear-MD	grams	35	mN	343.2	TAPPI T414
Tear-CD	grams	41	mN	402.1	TAPPI T414
Tensile-MD	lb/inch	34	kN/m	6.0	TAPPI T494
Tensile-CD	lb/inch	17	kN/m	3.0	TAPPI T494
Brightness	%	88	%	88.0	TAPPI T452

ADHESIVE

A general purpose acrylic emulsion used primarily with paper substrates.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.7	um(micrometer)	18.7	
Shear (1 x 1/2 x 1 kg)	hours	1.7	hours	1.7	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.6	grams/25 mm	714.3	CPD-52
Loop Tack Stain Steel	oz/sq inch	41	kg/645 sq mm	1.1	CPD-16
Min. App. Temp.	F	35	C	2	
Service Temp.	F	-40 TO 160	C	-40 TO 71	
FDA Compliance	21 CFR	175.105			

LINER

A white densified kraft sheet 41# (67 g/m²) with excellent point-to-point caliper control.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500 (3000 Sq Ft)	41.0	grams/sq meter	66.8	TAPPI T410
Caliper - Average	mil	2.400	um (micrometer)	61.0	TAPPI T411
Opacity	%	60.0	%	60.0	TAPPI T425
Tear-MD	grams	34.0	mN	333.4	TAPPI T414
Tear-CD	grams	39.0	mN	382.5	TAPPI T414
Tensile-MD	lb/inch	40.0	kN/m	7.0	TAPPI T494
Tensile-CD	lb/inch	17.1	kN/m	3.0	TAPPI T494

Issued: 07/03/24

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.