



PRODUCT INFORMATION

VALUT

Item #: S7847960

FSC-VALUE THERMAL TRANS

Approximate weight per MMSI: 88 lbs. Standard core size is 3 inches. Total caliper: 2.8 mils +/- 10%

FACESTOCK

A 42# (62 g/m²) top-coated, thermal transfer sheet that offers high performance at a lower cost. Strength and opacity are comparable to conventional thermal transfer facers. Exceptional print quality, especially for flood coating. FSC®-certified paper.

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|-----------------------------|-------------------------------|---------------|-----------------|--------------|-------------|
| Basis Weight | lbs/25X38-500 (3300 Sq Ft) | 41.8 | grams/sq meter | 61.9 | TAPPI T410 |
| Caliper - Average | mil | 2.8 | um (micrometer) | 71.1 | TAPPI T411 |
| Gloss | % | 12.0 | % | 12.0 | TAPPI T480 |
| Opacity | % | 87.0 | % | 87.0 | TAPPI T425 |
| Smoothness (PPS) Print Side | um | 2.2 | um | 2.2 | TAPPI T555 |
| Tear-MD | grams | 42.0 | mN | 411.9 | TAPPI T414 |
| Tear-CD | grams | 42.0 | mN | 411.9 | TAPPI T414 |
| Tensile-MD | lb/inch | 26.3 | kN/m | 4.6 | TAPPI T494 |
| Tensile-CD | lb/inch | 17.1 | kN/m | 3.0 | TAPPI T494 |
| Stiffness Taber-MD | gram cm/mN | 140.0 | gram cm/mN | 140 | TAPPI T543 |
| Stiffness Taber -CD | gram cm/mN | 90.0 | gram cm/mN | 90 | TAPPI T543 |
| Brightness | % | 86.0 | % | 86.0 | TAPPI T452 |

Issued: 11/21/24

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.