



PRODUCT INFORMATION

VALUT0027840SC

Item #: S8175760

FSC-VALUE THERMAL TRANS/278 ULTRA REMOVABLE ADH/40 SC LINER

Approximate weight per MMSI: 200 lbs. Standard core size is 3 inches. Total caliper: 5.6 mils +/- 10%

FACESTOCK

A 42# (62 g/m²) top-coated, thermal transfer sheet that offers high performance at a lower cost. Strength and opacity are comparable to conventional thermal transfer facers. Exceptional print quality, especially for flood coating. FSC®-certified paper.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	41.8	grams/sq meter	61.9	TAPPI T410
Caliper - Average	mil	2.8	um (micrometer)	71.1	TAPPI T411
Gloss	%	12.0	%	12.0	TAPPI T480
Opacity	%	87.0	%	87.0	TAPPI T425
Smoothness (PPS) Print Side	um	2.2	um	2.2	TAPPI T555
Tear-MD	grams	42.0	mN	411.9	TAPPI T414
Tear-CD	grams	42.0	mN	411.9	TAPPI T414
Tensile-MD	lb/inch	26.3	kN/m	4.6	TAPPI T494
Tensile-CD	lb/inch	17.1	kN/m	3.0	TAPPI T494
Stiffness Taber-MD	gram cm/mN	140.0	gram cm/mN	140	TAPPI T543
Stiffness Taber -CD	gram cm/mN	90.0	gram cm/mN	90	TAPPI T543
Brightness	%	86.0	%	86.0	TAPPI T452

ADHESIVE

Ultra-removable microsphere acrylic adhesive for paper face stocks. Adheres to, and removes cleanly from, a variety of substrates. Perfect for kiddie stickers, and short-term labeling such as price marking, promotions, and logistics.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.4	um(micrometer)	10.8	
Peel - 180 D SS 20 min	lb/inch	.235	grams/25 mm	104.9	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	.166	grams/25 mm	74.1	CPD-52
Peel - 180 D LDPE 20 min	lb/inch	.211	grams/25 mm	94.2	CPD-52
Peel - 180 D Glass 20 min	lb/inch	.140	grams/25 mm	62.5	CPD-52
Peel - 180 D Corrugated 20 min	lb/inch	.052	grams/25 mm	23.2	CPD-52
Loop Tack Stain Steel	oz/sq inch	7	kg/645 sq mm	.2	CPD-16
Loop Tack HDPE	oz/sq inch	7	kg/645 sq mm	.2	CPD-16
Loop Tack LDPE	oz/sq inch	8	kg/645 sq mm	.2	CPD-16
Loop Tack Corrugated	oz/sq inch	2	kg/645 sq mm	.1	CPD-16
Min. App. Temp.	F	20	C	-7	
Service Temp.	F	-10 TO 120	C	-23 TO 49	
FDA Compliance	21 CFR	175.105			

Notes

This adhesive is not intended for layflat applications.

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.



PRODUCT INFORMATION

LINER

A white densified kraft sheet 41# (67 g/m²) with excellent point-to-point caliper control.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500 (3000 Sq Ft)	41	grams/sq meter	66.8	TAPPI T410
Caliper - Average	mil	2.400	um (micrometer)	61.0	TAPPI T411
Opacity	%	60	%	60.0	TAPPI T425
Tear-MD	grams	34	mN	333.4	TAPPI T414
Tear-CD	grams	39	mN	382.5	TAPPI T414
Tensile-MD	lb/inch	40	kN/m	7.0	TAPPI T494
Tensile-CD	lb/inch	17	kN/m	3.0	TAPPI T494

Issued: 11/21/24

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.