



PRODUCT INFORMATION

0WCSW0074744PM

Item #: S8741852

FSC CLASSICCRESTSOLAR WH/PERMANENT ADHESIVE/44# POLYKRAFT LINER
Approximate weight per MMSI: 258 lbs. Standard core size is 3 inches. Total caliper: 8.2 mils +/- 10%

FACESTOCK

60# (89 g/m²) smooth, uncoated white paper with an excellent printing surface, high strength, and dimensional stability. Perfect for wine labels and other upscale products. FSC®-certified paper. *Registered Trademark of Neenah Paper, Inc.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	60.4	grams/sq meter	89.4	TAPPI T410
Caliper - Average	mil	4.4	um (micrometer)	111.8	TAPPI T411
Opacity	%	90	%	90.0	TAPPI T425
Smoothness Print Side	Sheffield Units	125	Sheffield Units	125.0	TAPPI T538

ADHESIVE

A general purpose, acrylic permanent that displays excellent adhesion over a broad temperature range while providing aggressive performance. Perfect for wine labeling, as it can withstand ice bucket conditions.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Shear (1 x 1/2 x 1 kg)	hours	1.2 TO 4.0	hours	1.2 TO 4.0	CPD-55
Peel - 180 D SS 20 min	lb/inch	2.2 TO 3.4	grams/25 mm	982.2 TO 1517.9	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	1.0 TO 1.9	grams/25 mm	446.5 TO 848.3	CPD-52
Peel - 180 D LDPE 20 min	lb/inch	1.5 TO 2.6	grams/25 mm	669.7 TO 1160.8	CPD-52
Peel - 180 D Glass 20 min	lb/inch	1.9 TO 3.0	grams/25 mm	848.3 TO 1339.4	CPD-52
Peel - 180 D Corrugated 20 min	lb/inch	0.8 TO 1.4	grams/25 mm	357.2 TO 625.0	CPD-52
Loop Tack Stain Steel	oz/sq inch	33 TO 47	kg/645 sq mm	.9 TO 1.3	CPD-16
Loop Tack HDPE	oz/sq inch	20 TO 36	kg/645 sq mm	.6 TO 1.0	CPD-16
Loop Tack LDPE	oz/sq inch	24 TO 38	kg/645 sq mm	.7 TO 1.1	CPD-16
Loop Tack Corrugated	oz/sq inch	13 TO 21	kg/645 sq mm	.4 TO .6	CPD-16
Loop Tack Glass	oz/sq inch	45 TO 56	kg/645 sq mm	1.3 TO 1.6	CPD-16
Min. App. Temp.	F	0	C	-18	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

LINER

A 44# (72 g/m²) natural kraft liner extrusion coated with polypropylene. Designed to prevent V-type tears and an excellent choice for high speed automatic applications. Commonly used in wine label applications.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500 (3000 Sq Ft)	43.5	grams/sq meter	70.9	TAPPI T410
Caliper - Average	mil	3.1	um (micrometer)	78.7	TAPPI T411
Smoothness-Felt Side	Sheffield Units	160	Sheffield Units	160.0	TAPPI T538
Smoothness-Wire Side	Sheffield Units	85	Sheffield Units	85.0	TAPPI T538
Tear-MD	grams	35	mN	343.2	TAPPI T414
Tear-CD	grams	50	mN	490.3	TAPPI T414
Tensile-MD	lb/inch	35	kN/m	6.1	TAPPI T494
Tensile-CD	lb/inch	13	kN/m	2.3	TAPPI T494

Issued: 06/27/26

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.