



0WEL80074712NB

Item #: S8756052

FSC ESTATE #8 WH VELLUM/PERMANENT ADHESIVE/1.2 MIL PET NO BACK COAT
Approximate weight per MMSI: 216 lbs. Standard core size is 3 inches. Total caliper: 6.7 mils +/- 10%

FACESTOCK

60# (89 g/m²) uncoated, white, wet strength paper. Maintains its integrity when wet. Designed for wine and other high-end labels, such as gourmet foods and cosmetics. *Registered Trademark of Neenah Paper, Inc. FSC®-certified paper.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500	60.0	grams/sq meter	88.8	TAPPI T410
Caliper - Average	mil	4.8	um (micrometer)	121.9	TAPPI T411
Moisture	%	5.5	%	5.5	TAPPI T412
Opacity	%	93.5	%	93.5	TAPPI T425
Smoothness Print Side	Sheffield Units	240	Sheffield Units	240.0	TAPPI T538
Tear-MD	grams	48	mN	470.7	TAPPI T414
Tear-CD	grams	51	mN	500.1	TAPPI T414
Tensile-MD	lb/inch	33.7	kN/m	5.9	TAPPI T494
Tensile-CD	lb/inch	22.4	kN/m	3.9	TAPPI T494
Brightness	%	92	%	92.0	TAPPI T452

ADHESIVE

A general purpose, acrylic permanent that displays excellent adhesion over a broad temperature range while providing aggressive performance. Perfect for wine labeling, as it can withstand ice bucket conditions.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.7	um(micrometer)	18.7	

LINER

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Average	mil	1.2	um (micrometer)	30.5	TAPPI T411
Tensile Film - MD	lb/sq inch	32,000	kg/sq cm	2249.6	ASTM D882
Tensile Film - TD	lb/sq inch	32,000	kg/sq cm	2249.6	ASTM D882
Elongation at Break - MD	%	130	%	130.0	ASTM D882
Elongation at Break - TD	%	100	%	100.0	ASTM D882
Shrinkage-MD	% 30 min @ 302 F	1.5	% 30 min @ 150 C	1.5	ISO 2469
Shrinkage-TD	% 30 min @ 302 F	.4	% 30 min @ 150 C	.4	ISO 2469
Area Yield	sq in/lb	16,805	sq m/kg	24.0	ASTM E252

Issued: 11/28/20

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions (found in the current Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book) in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho. Los Términos y Condiciones vigentes que regulan toda relación comercial de Green Bay Packaging Inc. - Coated Products Operations son los que se encuentran impresos en inglés en el último Libro de Precios. (Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book.)