



PRODUCT INFORMATION

0TTFP0758M12NB

Item #: S8863160

SELECT THERMAL TRANS FSC/758M PERMANENT ADHESIVE/1.2 MIL PET NO BACK COAT
Approximate weight per MMSI: 180 lbs. Standard core size is 3 inches. Total caliper: 4.75 mils +/- 10%

FACESTOCK

A 44# (65 g/m²) multi-purpose thermal transfer sheet. Premium coating for enhanced flexo-printed graphics.
FSC®-certified paper.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	44	grams/sq meter	65.1	TAPPI T410
Caliper - Average	mil	2.85	um (micrometer)	72.4	TAPPI T411
Opacity	%	87.0	%	87.0	TAPPI T425
Smoothness (PPS) Print Side	um	2.0	um	2.0	TAPPI T555
Tear-MD	grams	42	mN	411.9	TAPPI T414
Tear-CD	grams	42	mN	411.9	TAPPI T414
Tensile-MD	lb/inch	26	kN/m	4.6	TAPPI T494
Tensile-CD	lb/inch	17	kN/m	3.0	TAPPI T494
Stiffness Taber-MD	gram cm/mN	140.0	gram cm/mN	140.0	TAPPI T543
Stiffness Taber -CD	gram cm/mN	90.0	gram cm/mN	90.0	TAPPI T543
Brightness	%	86.5	%	86.5	TAPPI T452

ADHESIVE

An acrylic general purpose permanent adhesive with great die-cutting and stripping properties. Adheres well to many substrates, including corrugated.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.7	um(micrometer)	17.3	
Shear (1 x 1/2 x 1 kg)	hours	1.3	hours	1.3	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.582	grams/25 mm	706.3	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	1.4	grams/25 mm	625.0	CPD-52
Peel - 180 D LDPE 20 min	lb/inch	1.318	grams/25 mm	588.4	CPD-52
Peel - 180 D Glass 20 min	lb/inch	1.676	grams/25 mm	748.3	CPD-52
Peel - 180 D Corrugated 20 min	lb/inch	.83	grams/25 mm	370.6	CPD-52
Loop Tack Stain Steel	oz/sq inch	38	kg/645 sq mm	1.1	CPD-16
Loop Tack HDPE	oz/sq inch	23	kg/645 sq mm	.6	CPD-16
Loop Tack LDPE	oz/sq inch	20	kg/645 sq mm	.6	CPD-16
Loop Tack Corrugated	oz/sq inch	14	kg/645 sq mm	.4	CPD-16
Loop Tack Glass	oz/sq inch	35	kg/645 sq mm	1.0	CPD-16
Min. App. Temp.	F	35	C	2	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.



PRODUCT INFORMATION

LINER

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	1.200	um (micrometers)	30.5	ASTM D374
Tensile Film - MD	lb/sq inch	26300	kg/sq cm	1848.9	ASTM D882
Tensile Film - TD	lb/sq inch	28400	kg/sq cm	1996.5	ASTM D882
Haze	%	4	%	4.0	ASTM D1003

Issued: 12/21/24

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.