



PRODUCT INFORMATION

26WBU0010240SC

Item #: S9007360

2.6 MIL WHITE BOPP/FILMIC ADHESIVE/40 SC LINER

Approximate weight per MMSI: 187 lbs. Standard core size is 3 inches. Total caliper: 5.66 mils +/- 10%

FACESTOCK

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	2.56	um (micrometers)	65.0	ASTM D374
Gloss - Films	% @ 45 degrees	60	% @ 45 degrees	60.0	ASTM D2457
Opacity - Films	%	96	%	96.0	ASTM D589
Tensile Film - MD	lb/sq inch	13,000	kg/sq cm	913.9	ASTM D882
Tensile Film - TD	lb/sq inch	23,000	kg/sq cm	1616.9	ASTM D882
Stiffness-MD	Gurley (mg)	17.5	mN	.2	TAPPI T543
Stiffness-CD	Gurley (mg)	31.1	mN	.3	TAPPI T543
Elongation at Break - MD	%	150	%	150.0	ASTM D882
Elongation at Break - TD	%	45	%	45.0	ASTM D882
Dim. Stability - MD	% @ 275 F	4	% @ 135 C	4.0	ASTM D1204
Dim. Stability - TD	% @ 275 F	3	% @ 135 C	3.0	ASTM D1204
Elastic Modulus - MD	lb/sq inch	194,017	kg/sq cm	13639.4	ASTM D882
Elastic Modulus - TD	lb/sq inch	458,818	kg/sq cm	32254.9	ASTM D882
Surface Treatment-A Side	Dynes	40			ASTM D2578
Area Yield	sq in/lb	15,200	sq m/kg	21.7	ASTM E252

ADHESIVE

A clear, water-resistant, acrylic film adhesive with high tack and peel. Adheres to a wide variety of surfaces. Offers a good balance between wet-out and repositionability. Meets APR Critical Guidance Recognition for HDPE containers with specific facers.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.7	um(micrometer)	17.3	
Shear (1 x 1/2 x 1 kg)	hours	5.9	hours	5.9	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.8	grams/25 mm	803.6	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	.8	grams/25 mm	357.2	CPD-52
Peel - 180 D LDPE 20 min	lb/inch	.8	grams/25 mm	357.2	CPD-52
Peel - 180 D Glass 20 min	lb/inch	1.7	grams/25 mm	759.0	CPD-52
Peel - 180 D Corrugated 20 min	lb/inch	.5	grams/25 mm	223.2	CPD-52
Loop Tack Stain Steel	oz/sq inch	38	kg/645 sq mm	1.1	CPD-16
Loop Tack HDPE	oz/sq inch	27	kg/645 sq mm	.8	CPD-16
Loop Tack LDPE	oz/sq inch	25	kg/645 sq mm	.7	CPD-16
Loop Tack Corrugated	oz/sq inch	15	kg/645 sq mm	.4	CPD-16
Loop Tack Glass	oz/sq inch	28	kg/645 sq mm	.8	CPD-16
Min. App. Temp.	F	40	C	4	
Service Temp.	F	-40 TO 160	C	-40 TO 71	
FDA Compliance	21 CFR	175.105			

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.



PRODUCT INFORMATION

LINER

A white densified kraft sheet 41# (67 g/m²) with excellent point-to-point caliper control.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500 (3000 Sq Ft)	41	grams/sq meter	66.8	TAPPI T410
Caliper - Average	mil	2.400	um (micrometer)	61.0	TAPPI T411
Opacity	%	60	%	60.0	TAPPI T425
Tear-MD	grams	34	mN	333.4	TAPPI T414
Tear-CD	grams	39	mN	382.5	TAPPI T414
Tensile-MD	lb/inch	40	kN/m	7.0	TAPPI T494
Tensile-CD	lb/inch	17	kN/m	3.0	TAPPI T494

Issued: 07/03/24

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.