



# PRODUCT INFORMATION

**23WMU0075112NB**

**Item #: S9014360**

METALLIZED WHITE BOPP/751 PERMANENT ADHESIVE/1.2 MIL PET NO BACK COAT  
Approximate weight per MMSI: 169 lbs. Standard core size is 6 inches. Total caliper: 4.2 mils +/- 10%

## FACESTOCK

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	38.9	grams/sq meter	57.6	TAPPI T410
Caliper Average (Films)	mils	2.3	um (micrometers)	58.4	ASTM D374
Elongation at Break - MD	%	180	%	180.0	ASTM D882
Elongation at Break - TD	%	60	%	60.0	ASTM D882
Area Yield	sq in/lb	12200	sq m/kg	17.4	ASTM E252

## ADHESIVE

A paper and film compatible acrylic with good adhesion to many substrates. Excellent die-cutting and stripping. Exceptional mandrel hold.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.7	um(micrometer)	17.3	
Shear (1 x 1/2 x 1 kg)	hours	18.0	hours	18.0	CPD-55
Peel - 180 D SS 20 min	lb/inch	2.1	grams/25 mm	937.5	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	1.7	grams/25 mm	759.0	CPD-52
Peel - 180 D LDPE 20 min	lb/inch	2.1	grams/25 mm	937.5	CPD-52
Peel - 180 D Glass 20 min	lb/inch	1.7	grams/25 mm	759.0	CPD-52
Peel - 180 D Corrugated 20 min	lb/inch	.5	grams/25 mm	223.2	CPD-52
Loop Tack Stain Steel	oz/sq inch	52	kg/645 sq mm	1.5	CPD-16
Loop Tack HDPE	oz/sq inch	41	kg/645 sq mm	1.1	CPD-16
Loop Tack LDPE	oz/sq inch	25	kg/645 sq mm	.7	CPD-16
Loop Tack Corrugated	oz/sq inch	10.7	kg/645 sq mm	.3	CPD-16
Loop Tack Glass	oz/sq inch	60	kg/645 sq mm	1.7	CPD-16
Min. App. Temp.	F	45	C	7	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.



# PRODUCT INFORMATION

## LINER

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	1.2	um (micrometers)	30.5	ASTM D374
Tensile Film - MD	lb/sq inch	32,000	kg/sq cm	2249.6	ASTM D882
Tensile Film - TD	lb/sq inch	32,000	kg/sq cm	2249.6	ASTM D882
Elongation at Break - MD	%	130	%	130.0	ASTM D882
Elongation at Break - TD	%	100	%	100.0	ASTM D882
Haze	%	6.0	%	6.0	ASTM D1003
Shrinkage-MD	% 30 min @ 302 F	1.5	% 30 min @ 150 C	1.5	ISO 2469
Shrinkage-TD	% 30 min @ 302 F	.4	% 30 min @ 150 C	.4	ISO 2469
Elastic Modulus - MD	lb/sq inch	550,000	kg/sq cm	38665.0	ASTM D882
Elastic Modulus - TD	lb/sq inch	550,000	kg/sq cm	38665.0	ASTM D882
Area Yield	sq in/lb	16,805	sq m/kg	24.0	ASTM E252

Issued: 11/21/24

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.