



PRODUCT INFORMATION

018MT0720M12NB

Item #: S9036660

1.85MIL METALIZED TCBOPP/720M ALL TEMP ADHESIVE/1.2 MIL PET NO BACK COAT
Approximate weight per MMSI: 147 lbs. Standard core size is 6 inches. Total caliper: 3.65 mils +/- 10%

FACESTOCK

1.85 mil clear BOPP metalized on the back for durability. Top coated for print compatibility with water-based and UV flexo, and UV inkjet. Great stiffness for automatic application. Ideal for bright label graphics that will catch the eye of the consumer.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	28.8	grams/sq meter	42.6	TAPPI T410
Caliper Average (Films)	mils	1.85	um (micrometers)	47.0	ASTM D374
Elongation at Break - MD	%	180	%	180.0	ASTM D882
Elongation at Break - TD	%	55	%	55.0	ASTM D882
Area Yield	sq in/lb	16083.9	sq m/kg	23.0	ASTM E252

ADHESIVE

A versatile cold-temperature acrylic adhesive that adheres to many packaging materials in a broad range of temperatures. Faster stripping than many cold-temp adhesives. Meets the TLMI Recycling Protocol TLMI-LRP-2 for paper recycling compatibility.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.6	um(micrometer)	16.3	
Shear (1 x 1/2 x 1 kg)	hours	.6	hours	.6	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.5	grams/25 mm	669.7	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	1.0	grams/25 mm	446.5	CPD-52
Peel - 180 D Glass 20 min	lb/inch	1.7	grams/25 mm	759.0	CPD-52
Loop Tack Stain Steel	oz/sq inch	44	kg/645 sq mm	1.2	CPD-16
Loop Tack HDPE	oz/sq inch	35	kg/645 sq mm	1.0	CPD-16

LINER

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	1.200	um (micrometers)	30.5	ASTM D374
Tensile Film - MD	lb/sq inch	26300	kg/sq cm	1848.9	ASTM D882
Tensile Film - TD	lb/sq inch	28400	kg/sq cm	1996.5	ASTM D882
Haze	%	4	%	4.0	ASTM D1003

Issued: 11/21/24

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.