



PRODUCT INFORMATION

024TL0720M40SC

Item #: S9042760

2.4 MIL WHITE BOPP/720M ALL TEMP ADHESIVE/40 SC LINER

Approximate weight per MMSI: 190 lbs. Standard core size is 3 inches. Total caliper: 5.5 mils +/- 10%

FACESTOCK

A 2.4 mil glossy white BOPP top coated for ink adhesion. Has a distinctive pearlescent sheen. Excellent compatibility with UV curing inks and water based flexo ink systems. Label-Lyte is a Trademark of Jindal Films America.

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|--------------------------|----------------|---------------|------------------|--------------|-------------|
| Caliper Average (Films) | mils | 2.400 | um (micrometers) | 61.0 | ASTM D374 |
| Gloss - Films | % @ 45 degrees | 58 | % @ 45 degrees | 58.0 | ASTM D2457 |
| Opacity - Films | % | 88 | % | 88.0 | ASTM D589 |
| Elongation at Break - MD | % | 150 | % | 150.0 | ASTM D882 |
| Elongation at Break - TD | % | 43 | % | 43.0 | ASTM D882 |
| Area Yield | sq in/lb | 15400 | sq m/kg | 22.0 | ASTM E252 |

ADHESIVE

A versatile cold-temperature acrylic adhesive that adheres to many packaging materials in a broad range of temperatures. Faster stripping than many cold-temp adhesives. Meets the TLMI Recycling Protocol TLMI-LRP-2 for paper recycling compatibility.

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|---------------------------|------------|---------------|----------------|--------------|-------------|
| Caliper - Calculated | mils | 0.7 | um(micrometer) | 17.3 | |
| Shear (1 x 1/2 x 1 kg) | hours | .6 | hours | .6 | CPD-55 |
| Peel - 180 D SS 20 min | lb/inch | 1.5 | grams/25 mm | 669.7 | CPD-52 |
| Peel - 180 D HDPE 20 min | lb/inch | 1.0 | grams/25 mm | 446.5 | CPD-52 |
| Peel - 180 D Glass 20 min | lb/inch | 1.7 | grams/25 mm | 759.0 | CPD-52 |
| Loop Tack Stain Steel | oz/sq inch | 44 | kg/645 sq mm | 1.2 | CPD-16 |
| Loop Tack HDPE | oz/sq inch | 35 | kg/645 sq mm | 1.0 | CPD-16 |

LINER

A white densified kraft sheet 41# (67 g/m²) with excellent point-to-point caliper control.

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|-------------------|-------------------------------|---------------|-----------------|--------------|-------------|
| Basis Weight | lbs/24X36-500 (3000 Sq Ft) | 41.0 | grams/sq meter | 66.8 | TAPPI T410 |
| Caliper - Average | mil | 2.400 | um (micrometer) | 61.0 | TAPPI T411 |
| Opacity | % | 60.0 | % | 60.0 | TAPPI T425 |
| Tear-MD | grams | 34.0 | mN | 333.4 | TAPPI T414 |
| Tear-CD | grams | 39.0 | mN | 382.5 | TAPPI T414 |
| Tensile-MD | lb/inch | 40.0 | kN/m | 7.0 | TAPPI T494 |
| Tensile-CD | lb/inch | 17.1 | kN/m | 3.0 | TAPPI T494 |

Issued: 11/21/24

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.