



PRODUCT INFORMATION

56MSW0072012NB

Item #: S9106860

SILVER MET PAPER WS/ALL TEMP ADHESIVE/1.2 MIL PET

Approximate weight per MMSI: 203 lbs. Standard core size is 6 inches. Total caliper: 4.6 mils +/- 10%

FACESTOCK

56# (83 g/m²) top coated silver metalized paper. Wet strength for use in moist environments including refrigerated foods and chilled beverages. The metallic look makes a product's graphics stand out. Not recommended for HP Indigo Presses.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	56.1	grams/sq meter	83.0	TAPPI T410
Caliper - Average	mil	2.8	um (micrometer)	71.1	TAPPI T411
Tear-MD	grams	43	mN	421.7	TAPPI T414
Tear-CD	grams	45	mN	441.3	TAPPI T414
Tensile-MD	lb/inch	28.0	kN/m	4.9	TAPPI T494
Tensile-CD	lb/inch	18.9	kN/m	3.3	TAPPI T494

ADHESIVE

A soft, general purpose, all-temperature acrylic adhesive for paper and film labels. Adheres to a variety of packages in a broad range of temperatures. Meets the TLMI Recycling Protocol TLMI-LRP-2 for paper recycling compatibility.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Shear (1 x 1/2 x 1 kg)	hours	.2	hours	.2	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.5	grams/25 mm	669.7	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	1	grams/25 mm	446.5	CPD-52
Peel - 180 D Glass 20 min	lb/inch	1.7	grams/25 mm	759.0	CPD-52
Peel - 180 D Corrugated 20 min	lb/inch	.6	grams/25 mm	267.9	CPD-52
Loop Tack Stain Steel	oz/sq inch	44	kg/645 sq mm	1.2	CPD-16
Loop Tack HDPE	oz/sq inch	35	kg/645 sq mm	1.0	CPD-16
Loop Tack Corrugated	oz/sq inch	14	kg/645 sq mm	.4	CPD-16
Min. App. Temp.	F	-20	C	-29	
Service Temp.	F	-65 TO 180	C	-54 TO 82	
FDA Compliance	21 CFR	175.105			

LINER

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	1.200	um (micrometers)	30.5	ASTM D374
Tensile Film - MD	lb/sq inch	26300	kg/sq cm	1848.9	ASTM D882

Issued: 05/11/26

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.