



# PRODUCT INFORMATION

**26WCT0072012NB**

**Item #: S9125479**

2.6M WHI CAVITATED BOPP/720 ALL TEMP ADHESIVE/1.2 MIL PET NO BACK COAT  
Approximate weight per MMSI: 149 lbs. Standard core size is 6 inches. Total caliper: 4.38 mils +/- 10%

### FACESTOCK

2.6 mil white top-coated BOPP. It is compatible with water-based and UV flexo, and UV inkjet presses. Glossy look. Perfect for health and beauty aid, household care, and beverage labeling.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	2.600	um (micrometers)	66.0	ASTM D374
Gloss - Films	% @ 45 degrees	70	% @ 45 degrees	70.0	ASTM D2457
Opacity - Films	%	90	%	90.0	ASTM D589
Tensile Film - MD	lb/sq inch	14500	kg/sq cm	1019.4	ASTM D882
Tensile Film - TD	lb/sq inch	29000	kg/sq cm	2038.7	ASTM D882
Stiffness-MD	Gurley (mg)	23	mN	.2	TAPPI T543
Stiffness-CD	Gurley (mg)	45	mN	.4	TAPPI T543
Elongation at Break - MD	%	170	%	170.0	ASTM D882
Elongation at Break - TD	%	35	%	35.0	ASTM D882
Area Yield	sq in/lb	15500	sq m/kg	22.2	ASTM E252

### ADHESIVE

A soft, general purpose, all-temperature acrylic adhesive for paper and film labels. Adheres to a variety of packages in a broad range of temperatures. Meets the TLMI Recycling Protocol TLMI-LRP-2 for paper recycling compatibility.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.6	um(micrometer)	15.6	
Shear (1 x 1/2 x 1 kg)	hours	.2	hours	.2	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.5	grams/25 mm	669.7	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	1.0	grams/25 mm	446.5	CPD-52
Peel - 180 D LDPE 20 min	lb/inch	1.1	grams/25 mm	491.1	CPD-52
Peel - 180 D Glass 20 min	lb/inch	1.7	grams/25 mm	759.0	CPD-52
Peel - 180 D Corrugated 20 min	lb/inch	.6	grams/25 mm	267.9	CPD-52
Loop Tack Stain Steel	oz/sq inch	44	kg/645 sq mm	1.2	CPD-16
Loop Tack HDPE	oz/sq inch	35	kg/645 sq mm	1.0	CPD-16
Loop Tack LDPE	oz/sq inch	29	kg/645 sq mm	.8	CPD-16
Loop Tack Corrugated	oz/sq inch	14	kg/645 sq mm	.4	CPD-16
Min. App. Temp.	F	-20	C	-29	
Service Temp.	F	-65 TO 180	C	-54 TO 82	
FDA Compliance	21 CFR	175.105			

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.



# PRODUCT INFORMATION

## LINER

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	1.180	um (micrometers)	30.0	ASTM D374
Tensile Film - MD	lb/sq inch	32000	kg/sq cm	2249.6	ASTM D882
Tensile Film - TD	lb/sq inch	32000	kg/sq cm	2249.6	ASTM D882
Elongation at Break - MD	%	130	%	130.0	ASTM D882
Elongation at Break - TD	%	100	%	100.0	ASTM D882
Haze	%	6.0	%	6.0	ASTM D1003
Shrinkage-MD	% 30 min @ 302 F	1.5	% 30 min @ 150 C	1.5	ISO 2469
Shrinkage-TD	% 30 min @ 302 F	.4	% 30 min @ 150 C	.4	ISO 2469
Area Yield	sq in/lb	16805	sq m/kg	24.0	ASTM E252

Issued: 01/28/25

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.