

PRODUCT INFORMATION

060PR0027541WK

Item #:

S9156360

PREFERRED SEMI GLOSS FSC/275 ULTRA REMOVABLE ADH/41# WHITE KRAFT LINER Approximate weight per MMSI: 241 lbs. Standard core size is 3 inches. Total caliper: 6.2 mils +/- 10%

FACESTOCK

64# (94 g/m²) semi-gloss, multi-purpose litho with superior gloss and print qualities. Excellent print surface with flexo or offset. FSC®-certified paper.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Average	mil	3.100	um (micrometer)	78.7	TAPPI T411

ADHESIVE

Most universal acrylic microsphere adhering to corrugated, glass, metal, and plastics. No residue on glass or credit cards. Repositionable. Not recommended for small labels, or flood coated applications. Repulpable when applied to paper face stocks.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.4	um(micrometer)	10.1	
Shear (1 x 1/2 x 1 kg)	hours	.2	hours	.2	CPD-55
Peel - 180 D SS 20 min	lb/inch	.201	grams/25 mm	89.7	CPD-52
Peel - 180 D Glass 20 min	lb/inch	.116	grams/25 mm	51.8	CPD-52
Peel - 180 D Corrugated 20 min	lb/inch	.174	grams/25 mm	77.7	CPD-52
Loop Tack Stain Steel	oz/sq inch	9.73	kg/645 sq mm	.3	CPD-16
Loop Tack HDPE	oz/sq inch	4.0	kg/645 sq mm	.1	CPD-16
Loop Tack LDPE	oz/sq inch	4.7	kg/645 sq mm	.1	CPD-16
Loop Tack Corrugated	oz/sq inch	1.7	kg/645 sq mm	.0	CPD-16
Loop Tack Glass	oz/sq inch	3.0	kg/645 sq mm	.1	CPD-16
Min. App. Temp.	F	35	С	2	
Service Temp.	F	20 TO 120	С	-7 TO 49	
FDA Compliance	21 CFR	175.105			

Notes

Some streaking is normal with 275. Therefore, it is not recommended for small label or flood coat applications. We will honor claims if streaks are wider than 3/16 in.; or multiple smaller streaks spaced less than 3 in. apart. This adhesive is not intended for layflat applications.

LINER

A premium, 41# (66 g/m²) white kraft liner that is designed for roll-to-roll and fan-fold applications. Outstanding performance die cutting both paper and film.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500 (3000 Sq Ft)	40.5	grams/sq meter	66.0	TAPPI T410
Caliper - Average	mil	2.7	um (micrometer)	68.6	TAPPI T411
Tear-MD	grams	46.9	mN	459.9	TAPPI T414
Tear-CD	grams	54.0	mN	529.6	TAPPI T414
Tensile-MD	lb/inch	32.0	kN/m	5.6	TAPPI T494
Tensile-CD	lb/inch	14.3	kN/m	2.5	TAPPI T494

Issued: 08/31/25

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No solespectnations and constitute a guarantee or warranty. The company's standard Terms and Conditions in effect at the time of the sole shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún fipo de garantia. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.