

**GREEN BAY PACKAGING**

COATED PRODUCTS

PRODUCT INFORMATION

020MY0776S12NB**Item #:****S9187852**

2 ML CLEAR TC PET/PET RECYCLABLE ADHESIVE/1.2 MIL PET NO BACK COAT

Approximate weight per MMSI: 184 lbs. Standard core size is 6 inches. Total caliper: 3.8 mils +/- 10%

FACESTOCK

A very clear, top coated polyester film. Top coating allows for printing with most standard flexo and UV letterpress inks.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	2.0	um (micrometers)	50.8	ASTM D374
Tensile Film - MD	lb/sq inch	35,000	kg/sq cm	2460.5	ASTM D882
Tensile Film - TD	lb/sq inch	35,000	kg/sq cm	2460.5	ASTM D882
Elongation at Break - MD	%	150	%	150.0	ASTM D882
Elongation at Break - TD	%	110	%	110.0	ASTM D882
Haze	%	.7	%	.7	ASTM D1003
Dim. Stability - MD	% @ 275 F	1.0	% @ 135 C	1.0	ASTM D1204
Dim. Stability - TD	% @ 275 F	1.0	% @ 135 C	1.0	ASTM D1204
Area Yield	sq in/lb	9922	sq m/kg	14.2	ASTM D4321

ADHESIVE

A general purpose acrylic adhesive designed for PET recycling. Will wash off PET clamshells, bottles, and other containers during recycling leaving no adhesive residue behind. When combined with specific facers it has APR Critical Guidance Recognition.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.6	um(micrometer)	14.4	
Peel - 90 D PET 20 min	lb/inch	2.21	grams/25 mm	986.7	CPD-53
Shear (1 x 1/2 x 1 kg)	hours	7.98	hours	8.0	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.96	grams/25 mm	875.0	CPD-52
Loop Tack Stain Steel	oz/sq inch	55	kg/645 sq mm	1.5	CPD-16
Min. App. Temp.	F	25	C	-4	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

LINER

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Average	mil	1.2	um (micrometer)	30.5	TAPPI T411
Tensile Film - MD	lb/sq inch	32,000	kg/sq cm	2249.6	ASTM D882
Tensile Film - TD	lb/sq inch	32,000	kg/sq cm	2249.6	ASTM D882
Elongation at Break - MD	%	130	%	130.0	ASTM D882
Elongation at Break - TD	%	100	%	100.0	ASTM D882
Shrinkage-MD	% 30 min @ 302 F	1.5	% 30 min @ 150 C	1.5	ISO 2469
Shrinkage-TD	% 30 min @ 302 F	.4	% 30 min @ 150 C	.4	ISO 2469
Area Yield	sq in/lb	16,805	sq m/kg	24.0	ASTM E252

Issued: 10/15/25

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information, and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.

SPECIALISTS IN COATED SELF-ADHESIVE MATERIALS

3250 South Ridge Road • P. O. Box 19017 • Green Bay, WI 54307-9017 • USA • Phone: (920)-337-1800, 800-445-4269