



PRODUCT INFORMATION

018CT0976S92NB

Item #: S9214060

1.85 MIL TC CLEAR BOPP/APR WASHAWAY ALLTEMP ADH/92 GA SIL CTD PET LINER
Approximate weight per MMSI: 129 lbs. Standard core size is 6 inches. Total caliper: 3.27 mils +/- 10%

FACESTOCK

1.85 mil clear top-coated BOPP is compatible with water-based and UV flexo, and UV inkjet presses. Thinner for resource and shipping savings. Ultra clear for a no-label look. Perfect for health and beauty aid, household care, and beverage labeling.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	1.850	um (micrometers)	47.0	ASTM D374
Gloss - Films	% @ 45 degrees	85	% @ 45 degrees	85.0	ASTM D2457
Tensile Film - MD	lb/sq inch	19943	kg/sq cm	1402.0	ASTM D882
Tensile Film - TD	lb/sq inch	34954	kg/sq cm	2457.3	ASTM D882
Elongation at Break - MD	%	180	%	180.0	ASTM D882
Elongation at Break - TD	%	55	%	55.0	ASTM D882
Haze	%	2.5	%	2.5	ASTM D1003
Area Yield	sq in/lb	16083.9	sq m/kg	23	ASTM E252

ADHESIVE

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.5	um(micrometer)	13.7	
Loop Tack Stain Steel	oz/sq inch	38	kg/645 sq mm	1.1	CPD-16
Loop Tack PET	oz/sq inch	36	kg/645 sq mm	1.0	CPD-16
FDA Compliance	21 CFR	175.105			

LINER

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application. The benefits of this thinner gauge liner include reducing plastic use, decreasing shipping weight, and allowing more labels on a roll.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	.92	um (micrometers)	23.4	ASTM D374
Tensile Film - MD	lb/sq inch	32000	kg/sq cm	2249.6	ASTM D882
Tensile Film - TD	lb/sq inch	32000	kg/sq cm	2249.6	ASTM D882
Elongation at Break - MD	%	130	%	130.0	ASTM D882
Elongation at Break - TD	%	100	%	100.0	ASTM D882
Shrinkage-MD	% 30 min @ 302 F	1.5	% 30 min @ 150 C	1.5	ISO 2469
Shrinkage-TD	% 30 min @ 302 F	.4	% 30 min @ 150 C	.4	ISO 2469
Area Yield	sq in/lb	19800	sq m/kg	28.3	ASTM E252

Issued: 03/04/25

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.