



# PRODUCT INFORMATION

**026TL0095012NB**

**Item #: S9222160**

2.6 MIL WHITE TC BOPP/GP FILM ADHESIVE/1.2 MIL PET NO BACK COAT

Approximate weight per MMSI: 153 lbs. Standard core size is 6 inches. Total caliper: 4.4 mils +/- 10%

### FACESTOCK

A 2.6 mil glossy white BOPP top coated for ink adhesion. Has a distinctive pearlescent sheen. Excellent compatibility with UV curing inks and water based flexo ink systems. Label-Lyte is a Trademark of Jindal Films America.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	2.600	um (micrometers)	66.0	ASTM D374
Gloss - Films	% @ 45 degrees	68	% @ 45 degrees	68.0	ASTM D2457
Opacity - Films	%	89	%	89.0	ASTM D589
Elongation at Break - MD	%	200	%	200.0	ASTM D882
Elongation at Break - TD	%	50	%	50.0	ASTM D882
Area Yield	sq in/lb	14200	sq m/kg	20.3	ASTM E252

### ADHESIVE

General purpose filmic adhesive designed for prime label applications. High shear properties leading to excellent press convertibility. Provides good open time for label repositioning. Performs at application temperatures as low as 25°F.

Meets APR Preferred Design for Recycling on HDPE (colored) and PP substrates.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.6	um(micrometer)	14.4	
Shear (1 x 1/2 x 1 kg)	hours	100+	hours	100.0	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.8	grams/25 mm	803.6	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	1.2	grams/25 mm	535.7	CPD-52
Peel - 180 D LDPE 20 min	lb/inch	1.1	grams/25 mm	491.1	CPD-52
Peel - 180 D Glass 20 min	lb/inch	2.1	grams/25 mm	937.5	CPD-52
Peel - 180 D PET 20 min	lb/inch	2.57	grams/25 mm	1147.4	CPD-52
Loop Tack Stain Steel	oz/sq inch	45	kg/645 sq mm	1.3	CPD-16
Loop Tack HDPE	oz/sq inch	27	kg/645 sq mm	.8	CPD-16
Loop Tack LDPE	oz/sq inch	24	kg/645 sq mm	.7	CPD-16
Loop Tack Glass	oz/sq inch	46	kg/645 sq mm	1.3	CPD-16
Min. App. Temp.	F	25	C	-4	
Service Temp.	F	-40 TO 160	C	-40 TO 71	
FDA Compliance	21 CFR	175.105			

### LINER

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	1.200	um (micrometers)	30.5	ASTM D374
Tensile Film - MD	lb/sq inch	26300	kg/sq cm	1848.9	ASTM D882
Tensile Film - TD	lb/sq inch	28400	kg/sq cm	1996.5	ASTM D882
Haze	%	4	%	4.0	ASTM D1003

Issued: 10/10/24

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.