



# PRODUCT INFORMATION

**55SSG0758MPRLF**

**Item #: S9246460**

54# C1S SEMI GLOSS/758M PERMANENT ADHESIVE/3.2 ML LAYFLAT LINER

Approximate weight per MMSI: 267 lbs. Standard core size is 3 inches. Total caliper: 6.7 mils +/- 10%

### FACESTOCK

54# (78 g/m<sup>2</sup>) C1S bright blue-white semi-gloss. High strength property makes it ideal for wide web high-speed stripping and die-cutting. Smooth surface provides excellent printing with flexo, UV letterpress, and offset methods. FSC®-certified paper.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	55.0	grams/sq meter	81.4	TAPPI T410
Caliper - Average	mil	2.900	um (micrometer)	73.7	TAPPI T411
Gloss	%	68.0	%	68.0	TAPPI T480
Opacity	%	88.0	%	88.0	TAPPI T425
Tear-MD	grams	51.0	mN	500.1	TAPPI T414
Tensile-CD	lb/inch	16.0	kN/m	2.8	TAPPI T494
Brightness	%	88.0	%	88.0	TAPPI T452

### ADHESIVE

An acrylic general purpose permanent adhesive with great die-cutting and stripping properties. Adheres well to many substrates, including corrugated.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Shear (1 x 1/2 x 1 kg)	hours	1.3	hours	1.3	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.582	grams/25 mm	706.3	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	1.4	grams/25 mm	625.0	CPD-52
Peel - 180 D LDPE 20 min	lb/inch	1.318	grams/25 mm	588.4	CPD-52
Peel - 180 D Glass 20 min	lb/inch	1.676	grams/25 mm	748.3	CPD-52
Peel - 180 D Corrugated 20 min	lb/inch	.83	grams/25 mm	370.6	CPD-52
Loop Tack Stain Steel	oz/sq inch	38	kg/645 sq mm	1.1	CPD-16
Loop Tack HDPE	oz/sq inch	23	kg/645 sq mm	.6	CPD-16
Loop Tack LDPE	oz/sq inch	20	kg/645 sq mm	.6	CPD-16
Loop Tack Corrugated	oz/sq inch	14	kg/645 sq mm	.4	CPD-16
Loop Tack Glass	oz/sq inch	35	kg/645 sq mm	1.0	CPD-16
Min. App. Temp.	F	35	C	2	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.



# PRODUCT INFORMATION

## LINER

A premium, 53# (87 g/m<sup>2</sup>) white kraft liner. Suitable for roll-to-sheet and fan fold applications. Designed for four-color process printing on the back side. Can be used for die cutting both paper and film.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500 (3000 Sq Ft)	53.4	grams/sq meter	87.0	TAPPI T410
Caliper - Average	mil	3.2	um (micrometer)	81.3	TAPPI T411
Smoothness (PPS) Liner Release Side	um	2.5	um	2.5	TAPPI T555
Smoothness Backside	Sheffield Units	80	Sheffield Units	80.0	TAPPI T538
Tear-MD	grams	61.2	mN	600.2	TAPPI T414
Tear-CD	grams	66.3	mN	650.2	TAPPI T414
Tensile-MD	lb/inch	40	kN/m	7.0	TAPPI T494
Tensile-CD	lb/inch	18.9	kN/m	3.3	TAPPI T494
Brightness	%	84	%	84.0	TAPPI T452

Issued: 04/13/26

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.