



PRODUCT INFORMATION

021RX0063340SC

Item #: S9247360

3.0 MIL PHARMACY DT FSC/633 REMOVABLE ADHESIVE/40 SC LINER

Approximate weight per MMSI: 222 lbs. Standard core size is 3 inches. Total caliper: 6.05 mils +/- 10%

FACESTOCK

This 48# (71 g/m²), no phenols added, top-coated paper resists chemicals, including cleaners, hand sanitizers and lotions. Holds up in heat and humidity. Vital drug information remains legible under most handling and storage conditions. FSC®-certified paper.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	48.0	grams/sq meter	71.0	TAPPI T410
Caliper - Average	mil	3.050	um (micrometer)	77.5	TAPPI T411
Smoothness (PPS) Print Side	um	1.2	um	1.2	TAPPI T555
Tear-MD	grams	43	mN	421.7	TAPPI T414
Tear-CD	grams	44.0	mN	431.5	TAPPI T414
Tensile-MD	lb/inch	32.0	kN/m	5.6	TAPPI T494
Tensile-CD	lb/inch	16.0	kN/m	2.8	TAPPI T494
Brightness	%	90.0	%	90.0	TAPPI T452
Initial Activation Temp	F	201	C	94	ISO 1924
Effective Activation Temp	F	226	C	108	ISO 1924
Optimum Activation Temp	F	300	C	149	ISO 1924

ADHESIVE

An aggressive removable acrylic adhesive with a clean release for paper and film labels. It adheres to, and removes from, a wide variety of surfaces. Does not ghost. Good mandrel hold. Ideal for resealable closure labels.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.6	um(micrometer)	15.8	
Shear (1 x 1/2 x 1 kg)	hours	1.0	hours	1.0	CPD-55
Peel - 180 D SS 20 min	lb/inch	.76	grams/25 mm	339.3	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	.37	grams/25 mm	165.2	CPD-52
Peel - 180 D LDPE 20 min	lb/inch	.42	grams/25 mm	187.5	CPD-52
Peel - 180 D Glass 20 min	lb/inch	.97	grams/25 mm	433.1	CPD-52
Peel - 180 D Corrugated 20 min	lb/inch	.72	grams/25 mm	321.4	CPD-52
Peel - 180 D HDPE 24hr	lb/inch	.46	grams/25 mm	205.4	CPD-52
Peel - 180 D LDPE 24hr	lb/inch	.60	grams/25 mm	267.9	CPD-52
Peel - 180 D PET 24hr	lb/inch	1.05	grams/25 mm	468.8	CPD-52
Loop Tack Stain Steel	oz/sq inch	24	kg/645 sq mm	.7	CPD-16
Loop Tack HDPE	oz/sq inch	13	kg/645 sq mm	.4	CPD-16
Loop Tack LDPE	oz/sq inch	9	kg/645 sq mm	.3	CPD-16
Loop Tack Corrugated	oz/sq inch	6.7	kg/645 sq mm	.2	CPD-16
Loop Tack Glass	oz/sq inch	21	kg/645 sq mm	.6	CPD-16
Min. App. Temp.	F	30	C	-1	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.



PRODUCT INFORMATION

LINER

A white densified kraft sheet 41# (67 g/m²) with excellent point-to-point caliper control.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500 (3000 Sq Ft)	41	grams/sq meter	66.8	TAPPI T410
Caliper - Average	mil	2.400	um (micrometer)	61.0	TAPPI T411
Opacity	%	60	%	60.0	TAPPI T425
Tear-MD	grams	34	mN	333.4	TAPPI T414
Tear-CD	grams	39	mN	382.5	TAPPI T414
Tensile-MD	lb/inch	40	kN/m	7.0	TAPPI T494
Tensile-CD	lb/inch	17	kN/m	3.0	TAPPI T494

Issued: 04/08/25

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.