



PRODUCT INFORMATION

22PDE0075740SC

Item #: S9253852

PF PKG DELIVERY/TACKIFIED PERM ADH/40 SC LINER

Approximate weight per MMSI: 227 lbs. Standard core size is 3 inches. Total caliper: 6.2 mils +/- 10%

FACESTOCK

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	47.5	grams/sq meter	70.3	TAPPI T410
Caliper - Average	mil	3.1	um (micrometer)	78.7	TAPPI T411
Smoothness (PPS) Print Side	um	1.9	um	1.9	TAPPI T555
Tear-MD	grams	45.0	mN	441.3	TAPPI T414
Tensile-CD	lb/inch	17	kN/m	3.0	TAPPI T494
Brightness UV Excl	%	85	%		Tappi T571
Initial Activation Temp	F	235	C	113	ISO 1924
Effective Activation Temp	F	261	C	127	ISO 1924
Optimum Activation Temp	F	270	C	132	ISO 1924

ADHESIVE

A permanent acrylic adhesive with an aggressive bond to many surfaces, including low-energy plastics and corrugated. Harder adhesive for clean converting. Meets the TLMI Recycling Protocol TLMI-LRP-2 for paper recycling compatibility.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.7	um(micrometer)	17.7	
Shear (1 x 1/2 x 1 kg)	hours	5.2	hours	5.2	CPD-55
Peel - 180 D SS 20 min	lb/inch	2.32	grams/25 mm	1035.8	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	1.5	grams/25 mm	678.6	CPD-52
Peel - 180 D LDPE 20 min	lb/inch	1.8	grams/25 mm	803.6	CPD-52
Peel - 180 D Glass 20 min	lb/inch	2.2	grams/25 mm	991.1	CPD-52
Loop Tack Stain Steel	oz/sq inch	43	kg/645 sq mm	1.2	CPD-16
Loop Tack HDPE	oz/sq inch	41.0	kg/645 sq mm	1.1	CPD-16
Loop Tack LDPE	oz/sq inch	44	kg/645 sq mm	1.2	CPD-16
Loop Tack Corrugated	oz/sq inch	15.2	kg/645 sq mm	.4	CPD-16
Loop Tack Glass	oz/sq inch	33.0	kg/645 sq mm	.9	CPD-16
Min. App. Temp.	F	32	C	0	
Service Temp.	F	-58 TO 199	C	-50 TO 93	

LINER

A white densified kraft sheet 41# (67 g/m²) with excellent point-to-point caliper control.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500 (3000 Sq Ft)	41.0	grams/sq meter	66.8	TAPPI T410
Caliper - Average	mil	2,400	um (micrometer)	61.0	TAPPI T411
Opacity	%	60	%	60.0	TAPPI T425
Tear-MD	grams	34	mN	333.4	TAPPI T414
Tear-CD	grams	39	mN	382.5	TAPPI T414
Tensile-MD	lb/inch	40	kN/m	7.0	TAPPI T494
Tensile-CD	lb/inch	17	kN/m	3.0	TAPPI T494

Issued: 12/21/24

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.