



# PRODUCT INFORMATION

**023WT0976S12NB**

**Item #: S9267460**

2.3 MIL TC WHITE BOPP/APR WASHAWAY ALLTEMP ADH/1.2 MIL PET

Approximate weight per MMSI: 165 lbs. Standard core size is 6 inches. Total caliper: 4 mils +/- 10%

### FACESTOCK

2.3 mil solid white top-coated BOPP. Compatible with UV and water-based flexo, and UV inkjet printing; also hot stamping. Exceptional opacity. Backside treated for adhesive anchorage. Great stiffness for auto application. Ideal for prime labeling.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	38.9	grams/sq meter	57.6	TAPPI T410
Caliper Average (Films)	mils	2.3	um (micrometers)	58	ASTM D374
Gloss - Films	% @ 45 degrees	50	% @ 45 degrees	50.0	ASTM D2457
Opacity	%	87	%	87.0	TAPPI T425
Tensile Film - MD	lb/sq inch	20000	kg/sq cm	1406.0	ASTM D882
Tensile Film - TD	lb/sq inch	35000	kg/sq cm	2460.5	ASTM D882
Elongation at Break - MD	%	180	%	180.0	ASTM D882
Elongation at Break - TD	%	60	%	60.0	ASTM D882
Area Yield	sq in/lb	12200	sq m/kg	17.4	ASTM E252

### ADHESIVE

All-temperature acrylic adhesive designed for PET, Colored HDPE, and PP recycling. Will wash off PET clamshells, bottles, and other containers. Carries APR critical guidance approval for PET, Colored HDPE and PP recycling when paired with clear, white, and metalized BOPP films.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Shear (1 x 1/2 x 1 kg)	hours	1.8	hours	1.8	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.3	grams/25 mm	580.4	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	1.0	grams/25 mm	446.5	CPD-52
Peel - 180 D Glass 20 min	lb/inch	1.2	grams/25 mm	535.7	CPD-52
Peel - 180 D PET 20 min	lb/inch	1.4	grams/25 mm	625.0	CPD-52
Loop Tack Stain Steel	oz/sq inch	39	kg/645 sq mm	1.1	CPD-16
Loop Tack HDPE	oz/sq inch	32	kg/645 sq mm	.9	CPD-16
Loop Tack Glass	oz/sq inch	38	kg/645 sq mm	1.1	CPD-16
Loop Tack PET	oz/sq inch	39	kg/645 sq mm	1.1	CPD-16
Min. App. Temp.	F	-20	C	-29	
Service Temp.	F	-65 TO 180	C	-54 TO 82	
FDA Compliance	21 CFR	175.105			

### LINER

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	1.200	um (micrometers)	30.5	ASTM D374
Tensile Film - MD	lb/sq inch	26300	kg/sq cm	1848.9	ASTM D882

Issued: 06/14/26

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.