



PRODUCT INFORMATION

L32DT0LATP

Item #: S9271752

3.2 MIL LINERLESS DT FSC/ALL TEMP ADHESIVE

Approximate weight per MMSI: 107 lbs. Standard core size is 3 inches. Total caliper: 3.5 mils +/- 10%

FACESTOCK

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500 (3300 Sq Ft)	48.7	grams/sq meter	72.1	TAPPI T410
Caliper - Average	mil	3.200	um (micrometer)	81.3	TAPPI T411
Smoothness (PPS) Print Side	um	2.0	um	2.0	TAPPI T555
Tear-MD	grams	45.0	mN	441.3	TAPPI T414
Tensile-CD	lb/inch	17.1	kN/m	3.0	TAPPI T494
Stiffness-MD	Gurley (mg)	91.8	mN	.9	TAPPI T543

ADHESIVE

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Shear (1 x 1/2 x 1 kg)	hours	.4	hours	.4	CPD-55
Peel - 180 D SS 20 min	lb/inch	2.0	grams/25 mm	892.9	CPD-52
Peel - 180 D HDPE 20 min	lb/inch	0.90	grams/25 mm	401.8	CPD-52
Peel - 180 D LDPE 20 min	lb/inch	0.90	grams/25 mm	401.8	CPD-52
Peel - 180 D Glass 20 min	lb/inch	1.6	grams/25 mm	714.3	CPD-52
Peel - 180 D Corrugated 20 min	lb/inch	0.50	grams/25 mm	223.2	CPD-52
Loop Tack Stain Steel	oz/sq inch	24	kg/645 sq mm	.7	CPD-16
Loop Tack HDPE	oz/sq inch	19	kg/645 sq mm	.5	CPD-16
Loop Tack LDPE	oz/sq inch	19	kg/645 sq mm	.5	CPD-16
Loop Tack Corrugated	oz/sq inch	3.5	kg/645 sq mm	.1	CPD-16
Loop Tack Glass	oz/sq inch	26	kg/645 sq mm	.7	CPD-16
Min. App. Temp.	F	-20	C	-29	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

Issued: 06/12/26

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho.