

1MBSCPP15PET6UPN102 6-Up Narrow Coupon Pattern
Item #: SC510100
FACESTOCK

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|--------------------------------|---------------------|---------------|--------------|--------------|-------------|
| Yield | in ² /lb | 40,800 | sq meter/kg | 58.3 | ASTM E252 |
| Caliper Average (Films) | mil | 0.8 | um | 20.3 | ASTM D374 |
| Haze | % | 2 | % | 2 | ASTMD374 |
| Tensile Strength at break – MD | psi | 16,000 | kg/sq cm | 1,124.8 | ASTM D882 |
| Tensile Strength at break – TD | psi | 38,000 | kg/sq cm | 2,671.4 | ASTM D882 |
| Elongation at Break –MD | % | 150 | % | 150 | ASTM D882 |
| Elongation at Break – TD | % | 50 | % | 50 | ASTM D882 |

BREAK AWAY COATING

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|----------------------|-------|---------------|--------------|--------------|-------------|
| Caliper – Calculated | mils | 0.4 | UM | 10.2 | TAPPI T411 |
| Release Value | grams | 250 | grams | 250 | Supplier |

FACESTOCK

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|--------------------------------|---------------------|---------------|--------------|--------------|-------------|
| Yield | in ² /lb | 40,800 | sq meter | 58.3 | ASTM E252 |
| Caliper Average (Films) | mil | 0.8 | um | 20.3 | ASTM D374 |
| Haze | % | 2 | % | 2 | ASTMD374 |
| Tensile Strength at break – MD | psi | 16,000 | kg/sq cm | 1,124.8 | ASTM D882 |
| Tensile Strength at break – TD | psi | 38,000 | kg/sq cm | 2,671.4 | ASTM D882 |
| Elongation at Break –MD | % | 150 | % | 150 | ASTM D882 |
| Elongation at Break – TD | % | 50 | % | 50 | ASTM D882 |

ADHESIVE (00102)

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|--------------------|------------|---------------|--------------|--------------|-------------|
| Shear 1x1/2x1kg) | hrs | 5.9 | hrs | 5.9 | CPD-55 |
| Peel 180D SS 20min | lb/inch | 1.8 | grams/25mm | 803.6 | CPD-52 |
| Loop Tack SS | oz/sq inch | 38 | kg/645sq mm | 1.1 | CPD-16 |
| Min App Temp | F | 40 | C | 4 | |
| Service Temp | F | -40 to 160 | C | -40 to 71 | |

LINER (1.4 Mil Polyester)

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|--------------------------|------------|---------------|--------------|--------------|-------------|
| Yield | sq in/lb | 13,968 | sq m/kg | 20 | ASTM E252 |
| Caliper | mils | 1.4 | um | 35.6 | ASTM D374 |
| Haze | % | 6.5 | % | 6.5 | ASTM D1003 |
| Elongation at break – MD | % | 110 | % | 110 | ASTM D882 |
| Elongation at break – TD | % | 110 | % | 110 | ASTM D882 |
| Tensile – MD | lb/sq inch | 32,000 | kg/sg inch | 2249.6 | ASTM D882 |
| Tensile – CD | lb/sq inch | 32,000 | kg/sq inch | 2249.6 | ASTM D882 |

Notes – Shelf life of product is eight months when stored out of direct sunlight and in a cool dry area. Additional product info on next page.

Notes –

- Minimum Order is 3 MMSI
- Overrun/Underrun Tolerance +/- 10%
- Roll Width is 14.75”
- 5,000’ and 10,000’ Rolls
- Wind – Liner Out Unless Specified
- Shipped on the Round

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions (found in the current Green Bay Packaging Inc. – Coated Products Operations, Roll Printer Price Book) in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho. Los Términos y Condiciones vigentes que regulan toda relación comercial de Green Bay Packaging Inc. – Coated Products Operations son los que se encuentran impresos en inglés en el último Libro de Precios. (Green Bay Packaging Inc. – Coated Products Operations, Roll Printer Price Book.)

SPECIALISTS IN COATED SELF-ADHESIVE MATERIALS
ESPECIALISTAS EN MATERIALES AUTO-ADHESIVOS
3250 South Ridge Road • P. O. Box 19017 • Green Bay, WI 54307-9017 • USA
Phone: 001-(920)-337-1800, 800-445-4269, WI: 800-472-4442 • FAX: 001-(920)-337-1797, 800-705-0111